

Test Report

Report No. : AGC05443230803-001

SAMPLE NAME	Classic wine set in wooden box, Wine accessories set in tinbWine set in Bamboo box., Wine set in bamboo box, Cheese and wine set, Wine set in wine box	οx,
MODEL NAME	: IT2658, MO7843, MO8147, MO8293, MO8416, KC26	590
APPLICANT	: MID OCEAN BRANDS B.V	
STANDARD(S)	: Please refer to the following page(s).	
DATE OF ISSUE	: Aug. 17, 2023	







MID OCEAN BRANDS B.V

7/F, Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong.

: 6/F., Building 2, Sanwei Chaxi Industrial Park, Sanwei Community, Hangcheng Street, Bao'an District, Shenzhen, Guangdong, China

Report on the submitted sample(s) said to be:

:

Sample Name	:	Classic wine set in wooden box, Wine accessories set in tinbox,							
		Wine set in Bamboo box., Wine set in bamboo box,							
		Cheese and wine set, Wine set in wine box							
Model	:	IT2658, MO7843, MO8147, MO8293, MO8416, KC2690							
Vendor code	:	104438							
Country of Origin	:	CHINA							
Country of Destination	:	EUROPE							
Sample Received Date	:	Aug. 03, 2023							
Testing Period	:	Aug. 03, 2023 to Aug. 17, 2023							
Test Requested	:	Selected test(s) as requested by client.							

Approved by : Jessie ling

Liangdan, Jessie.Liang

Technical Director

Test Requested:	Report No.: AGC05443230803-001 Conclusion
Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 63 - Lead(Pb) Content	Pass
Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 23 -Cadmium(Cd) Content	Pass
Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50 - Polycyclic-aromatic Hydrocarbons (PAHs) Content	Pass
Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 51&52 - Phthalates Content	Pass
Regulation (EU) 2019/1021 on persistent organic pollutants (POPs) - Pentachlorophenol (PCP) Content	Pass
- Formaldehyde Release	Pass
Regulation 1935/2004/EC and Technical Guide on Metals and alloys used in food c of Council of Europe Resolution CM/Res(2013)9 - Specific migration of Heavy metal	contact materials Pass
Regulation 1935/2004/EC, Regulation(EU) No 10/2011 and its amendment Regula 2020/1245 and Regulation (EU) 2018/213 and Council of Europe Resolution AP (2 - Overall migration - Bisphenol A(BPA) content - Specific migration of Bisphenol A(BPA) - Specific migration of Formaldehyde	
DM-4B-COM-003-v01 -Volatile Organic Matter - Peroxide value - Specific Migration of Organotin (measured as Tin)	Pass Pass Pass
Reference to Regulation 1935/2004/EC, Regulation(EU) No.10/2011& LFGB §64 Part 8 -Pentachlorophenol (PCP) content	BVL B 82.02 Pass
As specified by client, to determine the Leachable Lead and Cadmium content in co with reference to Regulation 1935/2004/EC, NO.84/500/EEC and 2005/31/EC.	eramic Ware Pass

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

R



Report Revise Record							
Report Version	Report Version Issued Date Valid Version Notes						
/	Aug. 17, 2023	Valid	Initial release				



The photo of the sample



The photo of AGC05443230803-001 is for use only with the original report.

Test Point Description

Test point	Test point description
1-1	Red coating
1-2	Wooden box
1-3	Bamboo box
1-4	Silver Iron Box
1-5	Black sponge+Black sponge cover
1-6	Silver metal buckle
1-7	Gold metal buckle
1-8	Silver metal nail
1-9	Gold metal nail
1-10	Black fabric insider collar
1-11	Metal ring
1-12	Metal knife
1-13	Metal bottle opener
1-14	Metal screw bottle opener
1-15	Metal stopper
1-16	Top of metal stopper



Test point	Test point description
1-17	Metal pourer
1-18	Metal pouer plug
1-19	Black silicone
1-20	Yellow wooden handle (metal stopper)+Yellow wooden handle (knife)
1-21	Yellow wooden handle (metal pourer)+Yellow wooden handle (shovel)
1-22	Brown wood handle (metal stopper)+Brown wood handle (knife)
1-23	Metal shovel
1-24	Rivet of cheese tool
1-25	Metal top of thermometer
1-26	Thermometer
1-27	Bamboo cutting board



Note: N.D.=Not Detected (less than method detection limit), MDL = Method Detection Limit, 1mg/kg=0.0001%

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 63

- Lead(Pb) Content

Test Methods and Equipment: IEC 62321-5:2013; ICP-OES

Test Item(s)	Unit Limit	MDL	Test Result(s)			
Test Item(s)	Unit	Lımıt	MDL	1-1	1-2	1-3
Lead(Pb)	mg/kg	500	10	N.D.	N.D.	N.D.
Con	Conformity	Conformity	Conformity			

Test Item(s)	Unit Limi	Limit	Limit MDL -	Test Result(s)			
Test Item(s)	Unit	Liiiit	MDL	1-4	1-5	1-6	
Lead(Pb)	mg/kg	500	10	N.D.	N.D.	N.D.	
Con	Conformity	Conformity	Conformity				

Test Item(s)	Unit Limit	MDL	Test Result(s)			
Test Item(s)	Unit	Limit	MIDL	1-7	1-8	1-9
Lead(Pb)	mg/kg	500	10	N.D.	N.D.	N.D.
Co	Conformity	Conformity	Conformity			

Test Item(s)	Unit Limi	Limit	Limit MDL	Test Result(s)			
Test hem(s)	Unit	Limit	MDL	1-10	1-11	1-12	
Lead(Pb)	mg/kg	500	10	N.D.	N.D.	N.D.	
Cor	Conformity	Conformity	Conformity				

Test Item(s)	Unit Limit	MDL	Test Result(s)			
Test Item(s)	Unit	LIIIII	MDL	1-13	1-14	1-15
Lead(Pb)	mg/kg	500	10	N.D.	N.D.	121
Conclusion				Conformity	Conformity	Conformity

Test Item(s)	Unit Limit		MDI	Test Result(s)		
Test Item(s)	Unit	Lımıt	MDL	1-16	1-17	1-18
Lead(Pb)	mg/kg	500	10	N.D.	N.D.	N.D.
Conclusion				Conformity	Conformity	Conformity

Test Item(s) U	Unit	Limit	Limit MDL -	Test Result(s)			
	Unit	Unit Limit		1-19	1-20	1-21	
Lead(Pb)	mg/kg	500	10	N.D.	N.D.	N.D.	
Con	Conformity	Conformity	Conformity				

Test Item(s)	Unit Limit	MDL	Test Result(s)			
			1-22	1-23	1-24	
Lead(Pb)	mg/kg	500	10	N.D.	N.D.	20
Conclusion				Conformity	Conformity	Conformity



Test Item(s)	Unit	Limit	MDL	Test Result(s)		
Test ttem(s)	Unit	LIIIII	MDL	1-25	1-27	
Lead(Pb)	mg/kg	500	10	25	N.D.	
Co	Conformity	Conformity				

Remark:

1. As specified by client, the submitted samples were mixed to test, the test points: 1-5,1-20,1-21,1-22

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 23

-Cadmium(Cd) Content

Test Methods and Equipment: IEC 62321-5:2013; ICP-OES

Test Item(s)	Unit Limit	MDI	Test Result(s)			
	Unit	Init Limit	MDL	1-1	1-5	1-19
Cadmium(Cd)	mg/kg	100	10	N.D.	N.D.	N.D.
Conclusion				Conformity	Conformity	Conformity

Remark:

1. As specified by client, the submitted samples were mixed to test, the test points: 1-5

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50

- Polycyclic-aromatic Hydrocarbons (PAHs) Content

Test Methods and Equipment: Afps GS 2019:01 PAK; GC-MS

Test Item(a)	Unit Limit		MDL	Test Result(s)			
Test Item(s)	Unit	LIIIII	MDL	1-1	1-5	1-19	
Benzo[a]pyrene(BaP)	mg/kg	1	0.1	N.D.	N.D.	N.D.	
Benzo[e]pyrene(BeP)	mg/kg	1	0.1	N.D.	N.D.	N.D.	
Benzo[a]anthracene(BaA)	mg/kg	1	0.1	N.D.	N.D.	N.D.	
Benzo[b]fluoranthene(BbF)	mg/kg	1	0.1	N.D.	N.D.	N.D.	
Benzo[j]fluoranthene(BjFA)	mg/kg	1	0.1	N.D.	N.D.	N.D.	
Benzo[k]fluoranthene(BkF)	mg/kg	1	0.1	N.D.	N.D.	N.D.	
Chrysene(CHR)	mg/kg	1	0.1	N.D.	N.D.	N.D.	
Dibenzo[a,h]anthracene(DBA)	mg/kg	1	0.1	N.D.	N.D.	N.D.	
Con	Conformity	Conformity	Conformity				

Remark:

1. As specified by client, the submitted samples were mixed to test, the test points: 1-5



Report No.: AGC05443230803-001 Limit requirements of Polycyclic-aromatic Hydrocarbons (PAHs) (Unit: mg/kg)

Items	CAS No.	Extender oils or used for the production of tyres or parts of tyres	Any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity	Toys, including activity toys, and childcare articles, any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity
Benzo[a]pyrene(BaP)	50-32-8	≤1	≤ 1	≤ 0.5
Benzo[e]pyrene(BeP)	192-97-2	/	≤ 1	≤ 0.5
Benzo[a]anthracene(BaA)	56-55-3	/	≤ 1	≤ 0.5
Benzo[b]fluoranthene(BbF)	205-99-2	/	≤ 1	≤ 0.5
Benzo[j]fluoranthene(BjFA)	205-82-3	/	≤ 1	≤ 0.5
Benzo[k]fluoranthene(BkF)	207-08-9	/	≤ 1	≤ 0.5
Chrysene(CHR)	218-01-9	/	≤ 1	≤ 0.5
Dibenzo[a,h]anthracene(DBA)	53-70-3	/	≤ 1	≤ 0.5
Sum of BaP+ BeP+ BaA+ BbF+ BjFA+ BkF+ CHR+ DBA	/	≤ 10	/	/

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 51&52

- Phthalates Content

Test Methods and Equipment: IEC 62321-8:2017; GC-MS

Tast Itam(s)	Unit Limit		MDI	Test Result(s)			
Test Item(s)	Unit		MDL	1-1	1-5	1-19	
Diisobutyl phthalate (DIBP) CAS:84-69-5	%	0.1	0.005	N.D.	N.D.	N.D.	
Dibutyl phthalate (DBP) CAS:84-74-2	%	0.1	0.005	0.038	N.D.	N.D.	
Butylbenzyl phthalate (BBP) CAS:85-68-7	%	0.1	0.005	N.D.	N.D.	N.D.	
Di-(2-ethylhexyl) Phthalate (DEHP) CAS:117-81-7	%	0.1	0.005	N.D.	N.D.	N.D.	
Di-n-octyl phthalate (DNOP) CAS:117-84-0	%	/	0.005	N.D.	N.D.	N.D.	
Di-isononyl phthalate (DINP) CAS:28553-12-0, 68515-48-0	%	/	0.005	N.D.	N.D.	N.D.	
Di-isodecyl phthalate(DIDP) CAS:26761-40-0, 68515-49-1	%	/	0.005	N.D.	N.D.	N.D.	
Sum of DIBP +DBP+BBP+DEHP	%	0.1	/	0.038	N.D.	N.D.	
Sum of DNOP+DINP+DIDP	%	0.1	/	N.D.	N.D.	N.D.	
Con	clusion			Conformity	Conformity	Conformity	



Remark: 1. As specified by client, the submitted samples were mixed to test, the test points: 1-5

Toys and childcare articles	Each of DEHP, DBP, BBP, DIBP is less than 0.1% or the sum of DEHP+DBP+BBP+DIBP is less than 0.1%
Toys and childcare articles which can be placed in the mouth by children	The sum of DINP+DIDP+DNOP is less than 0.1%

Regulation (EU) 2019/1021 on persistent organic pollutants (POPs)

- Pentachlorophenol (PCP) Content

Test Methods and Equipment: EPA 3550C:2007 & EPA 8270E:2018; GC-MS

Test Item(s)	Unit Limit	MDL	Test Result(s)			
			1-2	1-3	1-20	
Pentachlorophenol (PCP)	mg/kg	5	5	N.D.	N.D.	N.D.
Conclusion				Conformity	Conformity	Conformity

Test Item(s)	Unit Limit	Limit	MDL	Test Result(s)			
		LIIIII		1-21	1-22	1-27	
Pentachlorophenol (PCP)	mg/kg	5	5	N.D.	N.D.	N.D.	
Con	Conformity	Conformity	Conformity				

Remark:

1. As specified by client, the submitted samples were mixed to test, the test points: 1-20,1-21,1-22

- Formaldehyde Release

Test Methods and Equipment: EN 717-3:1996; UV-Vis

Test Item(s)	l n1t	Client's	MDL	Test Result(s)		
		limit		1-2	1-3	1-20
Formaldehyde Release	mg/kg	80	1	36	7	2
Con	Conformity	Conformity	Conformity			

Test Item(a)	Unit	Unit Client's MDL		Test Result(s)		
Test Item(s)	Unit	limit	MDL	1-21	1-22	1-27
Formaldehyde Release	mg/kg	80	1	8	N.D.	7
Conclusion			Conformity	Conformity	Conformity	

Remark:

1. As specified by client, the submitted samples were mixed to test, the test points: 1-20,1-21,1-22

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.




Test Method: With reference to EDQM Technical Guide on Metals and alloys used in food contact materials 2013.

			Test Result(s)	Unit: m
Test Item(s)	Test condition/	MDL	$1^{\text{st}} + 2^{\text{nd}} \text{ extractives}$	Limit
	Equipment		1-15	
Barium (Ba)		0.1	N.D.	8.4
Copper (Cu)		0.1	N.D.	28
Iron (Fe)		0.1	N.D.	280
Tin (Sn)		0.1	N.D.	700
Chromium (Cr)		0.01	N.D.	1.75
Manganese (Mn)		0.1	N.D.	12.6
Zinc (Zn)		0.1	N.D.	35
Aluminium (Al)		0.1	3.568	35
Lithium (Li)		0.01	N.D.	0.336
Beryllium (Be)		0.005	N.D.	0.07
Vanadium (V)	Artificial tap water, 40°	0.005	N.D.	0.07
Nickel (Ni)	40°C, 24h ICP-OES	0.01	N.D.	0.98
Cobalt (Co)		0.01	N.D.	0.14
Arsenic (As)		0.002	N.D.	0.014
Molybdenum (Mo)		0.01	N.D.	0.84
Silver (Ag)		0.01	N.D.	0.56
Cadmium (Cd)		0.002	N.D.	0.035
Antimony (Sb)		0.01	N.D.	0.28
Mercury (Hg)		0.002	N.D.	0.021
Thallium (Tl)		0.0001	N.D.	0.0007
Lead (Pb)		0.01	N.D.	0.07
Conclusion		/	Conformity	/



			Test Result(s)	
Test Item(s)	Test condition/ Equipment	MDL	3 rd extractives	Limit
			1-15	
Barium (Ba)		0.1	N.D.	1.2
Copper (Cu)		0.1	N.D.	4
Iron (Fe)		0.1	N.D.	40
Tin (Sn)		0.1	N.D.	100
Chromium (Cr)		0.01	N.D.	0.25
Manganese (Mn)		0.1	N.D.	1.8
Zinc (Zn)		0.1	N.D.	5
Aluminium (Al)		0.1	N.D.	5
Lithium (Li)		0.01	N.D.	0.048
Beryllium (Be)		0.005	N.D.	0.01
Vanadium (V)	Artificial tap water,	0.005	N.D.	0.01
Nickel (Ni)		0.01	N.D.	0.14
Cobalt (Co)		0.01	N.D.	0.02
Arsenic (As)		0.002	N.D.	0.002
Molybdenum (Mo)		0.01	N.D.	0.12
Silver (Ag)		0.01	N.D.	0.08
Cadmium (Cd)		0.002	N.D.	0.005
Antimony (Sb)		0.01	N.D.	0.04
Mercury (Hg)		0.002	N.D.	0.003
Thallium (Tl)		0.0001	N.D.	0.0001
Lead (Pb)		0.01	N.D.	0.01
Conclusion		/	Conformity	/





Unit: mg/kg

			Test Result(s)	Unit: mg/k
Test Item(s)	Test condition/ Equipment	MDL	1 st + 2 nd extractives	Limit
	Equipment		1-17	
Barium (Ba)		0.1	N.D.	8.4
Copper (Cu)		0.1	N.D.	28
Iron (Fe)		0.1	N.D.	280
Tin (Sn)		0.1	N.D.	700
Chromium (Cr)		0.01	N.D.	1.75
Manganese (Mn)		0.1	N.D.	12.6
Zinc (Zn)		0.1	N.D.	35
Aluminium (Al)		0.1	N.D.	35
Lithium (Li)		0.01	N.D.	0.336
Beryllium (Be)		0.005	N.D.	0.07
Vanadium (V)	Artificial tap water, 40℃, 0.5h	0.005	N.D.	0.07
Nickel (Ni)	ICP-OES	0.01	N.D.	0.98
Cobalt (Co)		0.01	N.D.	0.14
Arsenic (As)		0.002	N.D.	0.014
Molybdenum (Mo)		0.01	N.D.	0.84
Silver (Ag)		0.01	N.D.	0.56
Cadmium (Cd)		0.002	N.D.	0.035
Antimony (Sb)		0.01	N.D.	0.28
Mercury (Hg)		0.002	N.D.	0.021
Thallium (Tl)		0.0001	N.D.	0.0007
Lead (Pb)		0.01	N.D.	0.07
Conclusion		/	Conformity	/



			Test Result(s)	
Test Item(s)	Test condition/ Equipment	MDL	3 rd extractives	Limit
	Equipment		1-17	
Barium (Ba)		0.1	N.D.	1.2
Copper (Cu)		0.1	N.D.	4
Iron (Fe)		0.1	N.D.	40
Tin (Sn)		0.1	N.D.	100
Chromium (Cr)		0.01	N.D.	0.25
Manganese (Mn)		0.1	N.D.	1.8
Zinc (Zn)		0.1	N.D.	5
Aluminium (Al)		0.1	N.D.	5
Lithium (Li)		0.01	N.D.	0.048
Beryllium (Be)		0.005	N.D.	0.01
Vanadium (V)	Artificial tap water,	0.005	N.D.	0.01
Nickel (Ni)		0.01	N.D.	0.14
Cobalt (Co)		0.01	N.D.	0.02
Arsenic (As)		0.002	N.D.	0.002
Molybdenum (Mo)		0.01	N.D.	0.12
Silver (Ag)		0.01	N.D.	0.08
Cadmium (Cd)		0.002	N.D.	0.005
Antimony (Sb)		0.01	N.D.	0.04
Mercury (Hg)		0.002	N.D.	0.003
Thallium (Tl)		0.0001	N.D.	0.0001
Lead (Pb)		0.01	N.D.	0.01
Conclusion		/	Conformity	/



Report No.: AGC05443230803-001 Unit: mg/kg

Test Item(s)			Test Result(s)	
	Test condition/ Equipment	MDL	1 st + 2 nd extractives	Limit
	Equipment		1-23	
Barium (Ba)		0.1	N.D.	8.4
Copper (Cu)		0.1	N.D.	28
Iron (Fe)		0.1	N.D.	280
Tin (Sn)		0.1	N.D.	700
Chromium (Cr)		0.01	N.D.	1.75
Manganese (Mn)		0.1	N.D.	12.6
Zinc (Zn)		0.1	N.D.	35
Aluminium (Al)		0.1	N.D.	35
Lithium (Li)		0.01	N.D.	0.336
Beryllium (Be)		0.005	N.D.	0.07
Vanadium (V)	Artificial tap water,	0.005	N.D.	0.07
Nickel (Ni)	− 70°C, 0.5h ICP-OES	0.01	N.D.	0.98
Cobalt (Co)		0.01	N.D.	0.14
Arsenic (As)		0.002	N.D.	0.014
Molybdenum (Mo)		0.01	N.D.	0.84
Silver (Ag)		0.01	N.D.	0.56
Cadmium (Cd)		0.002	N.D.	0.035
Antimony (Sb)		0.01	N.D.	0.28
Mercury (Hg)		0.002	N.D.	0.021
Thallium (Tl)		0.0001	N.D.	0.0007
Lead (Pb)		0.01	N.D.	0.07
Conclusion		/	Conformity	/



			Test Result(s)	
Test Item(s)	Test condition/ Equipment	MDL	3 rd extractives	Limit
			1-23	
Barium (Ba)		0.1	N.D.	1.2
Copper (Cu)		0.1	N.D.	4
Iron (Fe)		0.1	N.D.	40
Tin (Sn)		0.1	N.D.	100
Chromium (Cr)		0.01	N.D.	0.25
Manganese (Mn)		0.1	N.D.	1.8
Zinc (Zn)		0.1	N.D.	5
Aluminium (Al)		0.1	N.D.	5
Lithium (Li)		0.01	N.D.	0.048
Beryllium (Be)		0.005	N.D.	0.01
Vanadium (V)	Artificial tap water,	0.005	N.D.	0.01
Nickel (Ni)	−−−−−−−−−−−−−−−−−−−−−−−−−−−−−−−−−−−−−	0.01	N.D.	0.14
Cobalt (Co)		0.01	N.D.	0.02
Arsenic (As)		0.002	N.D.	0.002
Molybdenum (Mo)		0.01	N.D.	0.12
Silver (Ag)		0.01	N.D.	0.08
Cadmium (Cd)		0.002	N.D.	0.005
Antimony (Sb)		0.01	N.D.	0.04
Mercury (Hg)		0.002	N.D.	0.003
Thallium (Tl)		0.0001	N.D.	0.0001
Lead (Pb)		0.01	N.D.	0.01
Conclusion		/	Conformity	/



	Test l		
Test point	Overall migra	Conclusion	
	3% Acetic acid, 40°C,24h	50% Ethanol, 40°C,24h	
1-19	N.D.	N.D.	Conformity
Limit	10	10	/
MDL	5	5	/

- Bisphenol A(BPA) content

Test Item	Bisphenol A (BPA)
Limit(Client's Requirement) (mg/kg)	Absent
MDL(mg/kg)	0.1
Test Method/ Instrument	EPA 3540C:1996& EPA 8321B:2007/ LC-MS-MS

Test point	Test Result (mg/kg)	Conclusion
Test point	Bisphenol A (BPA)	Conclusion
1-19	N.D.	Conformity



	Test Result		
Test point	Specific migration of Bisphenol A(BPA)/ (mg/kg)	Conclusion	
	3% Acetic acid, 40°C,24h		
1-19	N.D.	Conformity	
Limit(Client's Requirement)	0.05	/	
MDL	0.02	/	

-Specific migration of Formaldehyde

		Test Result	
Т	est point	Specific migration of Formaldehyde/ (mg/kg)	Conclusion
		3% Acetic acid,40°C,0.5h	
	1 st migration	N.D.	Conformity
1-27	2 nd migration	N.D.	Conformity
	3 rd migration	N.D.	Conformity
	Limit	15	/
	MDL	5	/



Unit: %

Test item(s)	Test Condition	MDL	Result(s) 1-19	Limit
Volatile Organic Matter	200°C, 4h	0.1	0.29	0.5
Conclusion		/	Conformity	/

- Peroxide value

Unit: %

Test Item	MDL	Result(s) 1-19	Limit
Peroxide value	0.2	N.D.	Absent
Conclusion	/	Conformity	/

- Specific Migration of Organotin (measured as Tin)

	Test Result	
Test point	Specific Migration of Organotin (measured as Tin)/ (mg/kg)	Conclusion
	3% Acetic acid, EN 13130-2004	
1-19	N.D.	Conformity
Limit	0.1	/
MDL	0.01	/

-Pentachlorophenol (PCP) content

Test Item	Pentachlorophenol (PCP)
Limit (mg/kg)	0.15
MDL(mg/kg)	0.05
Test Method/ Instrument	ENISO15320-2011/ GC-MS

Test point	Test Result (mg/kg)	Conclusion
	Pentachlorophenol (PCP)	
1-27	N.D.	Conformity


Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.




Test Result(s) of Leachable Lead and Cadmium (NO.84/500/EEC and 2005/31/EC)

			U	nit: mg/dm ²
Test Item(s)	Test Condition/ Equipment	MDL	Result(s) 4% Acetic acid 1-26	Limit
Lead (Pb)	EN 1388-2:1996, 4%acetic acid 22°C, 24h/ ICP-OES	0.1	N.D.	0.8
Cadmium (Cd)		0.01	N.D.	0.07
Conclusion		/	Conformity	/

Test Flow Chart of Heavy Metal Content








Test Flow Chart of Polycyclic-aromatic Hydrocarbons (PAHs)




Test Flow Chart of Phthalates






Test Flow Chart of Pentachlorophenol (PCP)







Test Flow Chart of Formaldehyde Release



Conditions of Issuance of Test Reports

1. All samples and goods are accepted by the Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd. (the "Company") solely for testing and reporting in accordance with the following terms and conditions. The company provides its services on the basis that such terms and conditions constitute express agreement between the company and any person, firm or company requesting its services (the "Clients").

2. Any report issued by Company as a result of this application for testing services (the "Report") shall be issued in confidence to the Clients and the Report will be strictly treated as such by the Company. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of the Company. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by the Company to its customer, supplier or other persons directly concerned. The Company will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the Report, unless required by the relevant governmental authorities, laws or court orders.

3. The Company shall not be called or be liable to be called to give evidence or testimony on the Report in a court of law without its prior written consent, unless required by the relevant governmental authorities, laws or court orders.

4. In the event of the improper use of the report as determined by the Company, the Company reserves the right to withdraw it, and to adopt any other additional remedies which may be appropriate.

5. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Company.

6. The Company will not be liable for or accept responsibility for any loss or damage however arising from the use of information contained in any of its Reports or in any communication whatsoever about its said tests or investigations.7. Clients wishing to use the Report in court proceedings or arbitration shall inform the Company to that effect prior to submitting the sample for testing.

8. The Company is not responsible for recalling the electronic version of the original report when any revision is made to them. The Client assumes the responsibility to providing the revised version to any interested party who uses them.
9. Subject to the variable length of retention time for test data and report stored hereinto as otherwise specifically required by individual accreditation authorities, the Company will only keep the supporting test data and information of the test report for a period of six years. The data and information will be disposed of after the aforementioned retention period has elapsed. Under no circumstances shall we provide any data and information which has been disposed of after retention period. Under no circumstances shall we be liable for damage of any kind, including (but not limited to) compensatory damages, lost profits, lost data, or any form of special, incidental, indirect, consequential or punitive damages of any kind, whether based on breach of contract of warranty, tort (including negligence), product liability or otherwise, even if we are informed in advance of the possibility of such damages.

*** End of Report ***