


TEST REPORT

Test Report # 21A-001570(A1) Date of Report Issue: April 14, 2021
Date of Sample Received: April 8, 2021 Pages: Page 1 of 7

CLIENT INFORMATION:

Company: Mid Ocean Brands B.V.
Address: 7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong



SAMPLE INFORMATION:

Product Name: Cork Yoga Brick
Style No.: - Labeled Age Grade: -
Order No.(PO No.): - Client Request Age Grade: -
Country of Origin: - Recommended Age Grade: -
Country of Distribution: Europe Tested Age Grade: -
Model No.: MO6268
Composition/Main Material: cork
Buyer Name: Mid Ocean Brands B.V.
Supplier Name: 100396
Testing Period: 04/08/2021-04/14/2021

OVERALL RESULT:

PASS with information

Please refer to the following pages for test result summary and appropriate notes.

QIMA (HANGZHOU) TESTING CO., LTD.

Vicky Yu

Vicky Yu
Chemical Laboratory Supervisor



QIMA (HANGZHOU) TESTING CO., LTD. ♦ 4-5/F A2 BLDG NO. 1213 HUOJU SOUTH ROAD PUYAN STREET BINJIANG DISTRICT HANGZHOU CHINA

♦ Email: Labtesting@qima.com ♦ Tel: (86) 571 8999 7158.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the QIMA decision rule.

This test report may not be reproduced in whole or in part, without written approval of QIMA (Hangzhou) Testing Co., Ltd.

TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	Regulation (EC) No. 1907/2006 REACH Annex XVII, Item 63 Lead in Substrate Materials
Information only	Client's Requirement, Formaldehyde Release in resin-bonded wood
PASS	Regulation (EC) No. 2019/1021 Persistent Organic Pollutants, ANNEX I - Pentachlorophenol



DETAILED RESULTS:

Regulation (EC) No. 1907/2006 REACH Annex XVII, Item 63 Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal) and/or CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	---	---	---	---	Limit (mg/kg)
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Total Lead (Pb)	305	---	---	---	---	500
Conclusion	PASS	---	---	---	---	

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 15 mg/kg)



DETAILED RESULTS:

Client's Requirement, Formaldehyde Release in resin-bonded wood

Test Method: EN 717-3:1996
 Analytical Method: Ultraviolet-Visible Spectrophotometry

Specimen No.	1	---	---	---	Limit (mg/kg)
Test Item CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Formaldehyde 50-00-0	ND	---	---	---	
Conclusion	Information only	---	---	---	

Note:
 mg/kg = Milligrams per kilogram
 NA = Not applicable
 LT = Less than
 ND = Not detected (Reporting Limit = 16 mg/kg)



DETAILED RESULTS:

Regulation (EC) No. 2019/1021 Persistent Organic Pollutants, ANNEX I - Pentachlorophenol

Test Method: CEN/TR 14823:2003

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.	1	---	---	---	Limit (mg/kg)
Test Item CAS No.	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Pentachlorophenol (PCP) 87-86-5	ND	---	---	---	Not detected
Conclusion	PASS	---	---	---	

Note:

mg/kg = Milligrams per kilogram

LT = Less than

ND = Not detected (Reporting Limit = 1 mg/kg)



SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Brown cork	Yoga Brick



SAMPLE PHOTO:



-End Report-

