

TEST REPORT

MID OCEAN BRANDS B.V.

Technical Report:	(3222)092-0157
Date Received:	Apr.02,2022

Apr.13,2022 Page 1 of 5

MID OCEAN BRANDS B.V. 7/F., KINGS TOWER, 111 KING LAM STREET, CHEUNG SHA WAN, KOWLOON, HONG KONG

SAMPLE INFORMATION:

Sample Description:	24PCS STATIONERY SET、 67PCS STATIONERY SE T	Sample Quantity:	N/A
Vendor:	111041	Style No(s):	MO8249、IT2369
Manufacturer:	N/A	SKN/SKU No.:	N/A
Buyer:	N/A	PO No.:	N/A
Labeled Age Grade:	N/A	Ref #:	N/A
Appropriate Age Grade:	N/A	Country of Origin:	N/A
Client Specified Age Grade:	N/A	Assortment No.:	N/A
Tested Age Grade:	N/A	Country of Destination:	N/A
UPC Code:	N/A	Color :	N/A

EXECUTIVE SUMMARY:

TEST REQUESTED	CONCLUSION
Formaldehyde Release from Wood	DATA

BVCPS (ZHEJIANG) GENERAL CONTACT INFORMATION FOR THIS REPORT

:

TELEPHONE NO. E-MAIL : 86-574-87091207 / 87091330 Heben.He@bureauveritas.com /Allen He@bureauveritas.com

Bureau Veritas Testing Technical Service (Zhejiang) Co., Ltd

Heber He

Heben He Technical Supervisor (HARDLINE AND TOY DIVISION)

This report is governed by, and incorporates by reference, CPS Conditions of Service as posted at the date of issuance of this report at http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/terms-conditions/and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with trespect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the 10 from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty is only provided upon request for accredited tests. You have 60 days from date of issuance of this report to notify us of any material error or omission caused by our negligence or if your equite uncertainty; provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the preseribed time shall constitute you unqualified acceptance of the completeness of the tests conducted and the correctness of the report contents.



MID OCEAN BRANDS B.V. Technical Report: **(3222)092-0157** Apr.13,2022 Page 2 of 5

Tested Component(s) Breakdown List

Test Item	Description	Location	Style
1	Beige wood	-	-

Formaldehyde Release from Wood

Test Method : EN 717-3: 1996

Parameter	Unit	Result	Maximum
		1	Allowable Limit
Moisture Content	%	7.3	-
Formaldehyde	mg/kg	ND	-
Conclusion	-	DATA	-

Note / Key:

ND = Not detected

Detection Limit (mg/kg) : 10


% = percent

mg/kg = milligram(s) formaldehyde per kilogram oven-dry board



MID OCEAN BRANDS B.V. Technical Report: **(3222)092-0157** Apr.13,2022 Page 3 of 5

SAMPLE REFERENCE PHOTO:





MID OCEAN BRANDS B.V. Technical Report: **(3222)092-0157** Apr.13,2022 Page 4 of 5





MID OCEAN BRANDS B.V. Technical Report: **(3222)092-0157** Apr.13,2022 Page 5 of 5



-- END OF REPORT --