



TEST REPORT

Report No. : WTF22F09192453C

Applicant..... : Mid Ocean Brands B.V.

Address : 7/F., Kings Tower, 111 King Lam Street, Cheung Sha

Wan, Kowloon, Hong Kong

Manufacturer: 107927

Sample Name: Trolley backpack

Sample Model.....: MO9179

Date of Receipt sample: 2022-09-22

Testing period : 2022-09-22 to 2022-09-29

Date of Issue : 2022-09-30

Test Result..... Refer to next page (s)

Prepared By: Waltek Testing Group (Foshan) Co., Ltd.

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City, Chencun, Shunde District, Foshan, Guangdong, China
Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Signed for and on behalf of Waltek Testing Group (Foshan) Co., Ltd.

Swing.Liang



Test Conclusion

Test Requested :: In accordance with the RoHS Directive 2011/65/EU and its amendment (EU) No. 2015/863.

Test Method :: 1) With reference to IEC 62321-2:2021, disassembly, disjunction and mechanical sample preparation
2) With reference to IEC 62321-3-1:2013, screening - Lead, mercury, cadmium, total chromium and total bromine by X-ray fluorescence spectrometry

3) With reference to IEC 62321-4:2013+AMD1:2017 CSV, determination of Mercury by ICP-OES

4) With reference to IEC 62321-5:2013, determination of Lead and Cadmium by ICP-OES

5) With reference to IEC 62321-7-2: 2017 and IEC 62321-7-1: 2015, determination of Hexavalent Chromium by UV-Vis

6) With reference to IEC 62321-6:2015, determination of PBBs and PBDEs by GC-MS

7) With reference to IEC 62321-8:2017, determination of Phthalates content by GC-MS.

Pass (Based on the performed tests on the submitted samples, the results comply with the RoHS Directive 2011/65/EU and its amendment (EU) No. 2015/863)





Sample Photo(s):





MANAGE LE CHE



Test Results:

1. Lead, Mercury, Cadmium, Hexavalent Chromium, PBBs and PBDEs

Part	a state of	£ ,	Res	ult of 2	KRF	24	Result of Wet Chemica
No.	Part Description	Cd	Pb	Hg	Cr	Br	Testing (mg/kg)
×1 ,	Black soft plastic shell	BL	BL	BL	BL	BL	NA WITE
2	Black plastic jacket (USB socket)	BL	BL	BL	BL	BL	NA COL
3.78	Black plastic core (USB socket)	BL	BL	BL	BL	BL	of NACO
4	Silvery metal sheet (USB socket)	BL	BL	BL	BL	70 (16)	NA NA
5	White plastic sheet (USB socket)	BL	BL	BL	BL	IN	PBBs : ND PBDEs : ND
6	Solder (USB socket)	BL	BL	BL	BL	 t	NA
7	Silvery metal pin (USB socket)	BL	BL	BL	BL	7	NA
8	Black plastic wire jacket	BL	BL	BL	BL	BL	NA
9	Green plastic wire covering	BL	BL	BL	BL	BL	MILL MA NA
10	Black plastic wire covering	BL	BL	BL	BL	BL	NA
11	Red plastic wire covering	BL	BL	BL	BL	BL	NA
12	White plastic wire covering	BL	BL	BL	BL	BL	NA WA
13	Coppery metal wire	BL	BL	BL	BL	MIZEK.	untitle until NA until u
14	Black plastic jacket (USB plug)	BL	BL	BL	BL	BL	LIET WALLET W
15	Silvery metal shell (USB plug)	BL	BL	BL	BL	k <u></u> vi	et unitet NAT unite
16	White plastic sheet (USB plug)	BL	BL	BL	BL	BL	antitt un NA untitet
17	Solder (USB plug)	BL	BL	BL	BL	LI EN	NA NA NA
18	Golden-silvery metal pin (USB plug)	BL	BL	BL	BL		THE THE NAME OF



Remark:

(1) Results are obtained by EDXRF for primary screening, and further chemical testing by ICP (for Cd, Pb, Hg), UV-VIS (for Cr⁶⁺) and GC-MS (for PBBs, PBDEs) is recommended to be performed, if the concentration exceeds the below warning value according to IEC 62321-3-1: 2013 (unit: mg/kg)

Element	Polymer	Metal	Composite Materials
Cd	BL \leq (70-3 σ) $<$ IN $<$ (130+3 σ) \leq OL	BL \leq (70-3 σ) $<$ IN $<$ (130+3 σ) \leq OL	LOD < IN < (150+3σ) ≤ OL
Pb	$BL \le (700-3\sigma) < IN < (1300+3\sigma) \le OL$	$BL \le (700-3\sigma) < IN < (1300+3\sigma) \le OL$	BL ≤ (500-3σ) < IN < (1500+3σ) ≤ OL
Hg	$BL \le (700-3\sigma) < IN < (1300+3\sigma) \le OL$	$BL \le (700-3\sigma) < IN < (1300+3\sigma) \le OL$	BL \leq (500-3 σ) $<$ IN $<$ (1500+3 σ) \leq OL
Cr	BL ≤ (700-3σ) < IN	BL ≤ (700-3σ) <in< td=""><td>BL ≤ (500-3σ) < IN</td></in<>	BL ≤ (500-3σ) < IN
Br	BL ≤ (300-3σ) < IN	- 1 1 1 1	BL ≤ (250-3σ) < IN

BL= Below Limit

OL= Over Limit

LOD = Limit of Detection

-- = Not Regulated

- (2) "IN" expresses the inconclusive region, and further chemical testing to confirm whether it complies with the requirement of RoHS Directive.
- (3) The XRF screening test for RoHS elements the reading may be different to the actual content in the sample be of non-uniformity composition.
- (4) mg / kg =milligram per kilogram=ppm, μg/cm²= Micrograms per square centimetre.
- (5) ND = Not Detected or lower than limit of quantitation.
- (6) NA = Not Applicable, as the XRF screening test result was below the limit or as the XRF screening directly determine that test result was over the limit, it was not need to conduct the wet chemical testing.
- (7) LOQ = Limit of quantitation.

Test Items	Pb	Cd	Hg	С	r ^{o+}	PBB	PBDE
Units	mg/kg	mg/kg	mg/kg	mg/kg	µg/cm ²	mg/kg	mg/kg
LOQ	2	2 +	2	8	0.1	5	5

The LOQ for single compound of PBBs and PBDEs is 5mg/kg, LOQ of Cr⁶⁺ for polymer and composite sample is 8mg/kg and LOQ of Cr⁶⁺ for metal sample is 0.1µg/cm².

(8) RoHS Requirement

Restricted Substances	Limits		
Cadmium (Cd)	0.01% (100 mg/kg)		
Lead (Pb)	0.1% (1000 mg/kg)		
Mercury (Hg)	0.1% (1000 mg/kg)		
Chromium (VI) (Cr ⁶⁺)	0.1% (1000 mg/kg)		
Polybrominated Biphenyls (PBBs)	0.1% (1000 mg/kg)		
Polybrominated Diphenyl Ethers (PBDEs)	0.1% (1000 mg/kg)		



(9) According to IEC 62321-7-1:2015, determined of Cr⁶⁺ on metal sample by boiling water extraction test method, and result is shown as Positive/Negative.

Boiling water extraction:

Negative = Absence of Cr⁶⁺ coating, the detected concentration in boiling water extraction solution is less than 0.10ug/cm².

Positive = Presence of Cr⁶⁺ coating, the detected concentration in boiling water extraction solution is greater than 0.13ug/cm².

Information on storage conditions and production date of the tested sample is unavailable and thus Cr⁶⁺ results represent status of the sample at the time of testing.

(10) Abbreviation:

"Pb" denotes Lead, "Cd" denotes Cadmium, "Hg" denotes Mercury, "Cr" denotes Chromium, "Cr (VI)" denotes Hexavalent Chromium, "Br" denotes Bromine, "PBBs" denotes Total Polybrominated Biphenyls, "PBDEs" denotes Total Polybrominated Diphenyl Ethers.

2. Phthalates:

Serial	- TEN DATE NO OLIVE SOLI	Result (mg/kg)					
No.	Part No.	DBP	BBP	DEHP	DIBP		
T01	18 18 18 18 18 18 18 18 18 18 18 18 18 1	ND	ND	ND	L ND		
T02	and the same and	ND	ND ND	ND	ND		
T03	3 4	ND	ND	ND	ND		
T04	4	40,		- Ek	Will Will Wil		
T05	5+16 [△]	ND	ND	ND	ND		
T06	6	K ("	,	+	et the tie		
T07	7	J+ 3 ²⁷ 3	CULL MU	me - me	24, 20,		
T08	it it is	ND	ND	ND	- ND		
T09	9	ND	ND	ND	ND		
T10	10	ND	ND	ND	ND -		
T11	pri we 11 m	ND	ND.	ND	ND ND		
T12	12 /	ND	ND	ND	ND		
T13	13	71	A	et et .	JER JE NI		
T14	14	ND	ND	WND W	ND		
T15	15	n n - n		, , , , , , , ,	A TEN TEN		
T16	17	ar at S		with - with	me -m		
T17	18	and and	44 24.		1 - 1t		

Note:

- (1) mg/kg = milligram per kilogram= ppm
- (2) ND = Not Detected or lower than limit of quantitation.
- (3) -- = Not Regulated.
- (4) LOQ = Limit of quantitation.

Test Items	DBP	BBP	DEHP	DIBP
Units	mg/kg	mg/kg	mg/kg	mg/kg
LOQ	50	50	50	50



(5) Abbreviation:

"DBP" denotes Dibutyl phthalate, "BBP" denotes Benzyl butyl phthalate (BBP), "DEHP" denotes Bis(2-ethylhexyl)-phthalate, "DIBP" denotes Diisobutyl phthalate, "PHT" denotes Phthalates.

(6) RoHS requirement


Restricted Substances	Limits
Dibutyl phthalate (DBP)	0.1% (1000 mg/kg)
Benzyl butyl phthalate (BBP)	0.1% (1000 mg/kg)
Di(2-ethylhexyl) phthalate (DEHP)	0.1% (1000 mg/kg)
Di-iso-butyl phthalate (DIBP)	0.1% (1000 mg/kg)

(7) "△"= As client's requirement, the testing was conducted based on mixed components. Results are calculated by the minimum weight of mixed components.






Measurement Flowchart:





Photograph(s) of parts tested:



Remarks:

- 1. The results shown in this test report refer only to the sample(s) tested;
- 2. This test report cannot be reproduced, except in full, without prior written permission of the company;
- 3. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver:
- 4. The Applicant name and Address, the sample(s) and sample information was/were provided by the applicant who should be responsible for the authenticity which Waltek hasn't verified;
- 5. If the report is not stamped with the accreditation recognized seal, it will only be used for scientific research, education, and internal quality control activities, and is not used for the purpose of issuing supporting data to the society.
- 6. The sample material information (Model No. information) is provided by client, not verified by test laboratory. The samples of reference Model No. are not tested. Test laboratory not responsible for the accuracy, appropriateness, completeness and authenticity of the information provided by client.

===== End of Report =====