

Test Report

Report No. : AGC05443230802-001

SAMPLE NAME : 8 Digit bamboo calculator

MODEL NAME : MO6215

APPLICANT: MID OCEAN BRANDS B.V

STANDARD(S) : Please refer to the following page(s).

DATE OF ISSUE : Aug. 09, 2023

Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd.





Applicant : MID OCEAN BRANDS B.V

Address : 7/F, Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong.

Test Site : 6/F., Building 2, Sanwei Chaxi Industrial Park, Sanwei Community, Hangcheng Street,

Bao'an District, Shenzhen, Guangdong, China

Report on the submitted sample(s) said to be:

Sample Name : 8 Digit bamboo calculator

Model : MO6215 Vendor code : 114628

Sample Received Date : Aug. 03, 2023

Testing Period : Aug. 03, 2023 to Aug. 07, 2023

Test Requested : Selected test(s) as requested by client.

Test Requested: Conclusion

2011/65/EU (RoHS) and its amendment directive (EU) 2015/863

- Pb, Cd, Hg, Cr⁶⁺, PBBs, PBDEs, DBP, BBP, DEHP, DIBP

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50

- Polycyclic-aromatic Hydrocarbons (PAHs) Content

Regulation (EU) 2019/1021 on persistent organic pollutants (POPs)

- Pentachlorophenol (PCP) Content

- Formaldehyde Release Pass

Approved by : Jossie Liang

Liangdan, Jessie.Liang

Report No.: AGC05443230802-001

Pass

Pass

Pass

Technical Director




Report Revise Record


Report Version	Issued Date	Valid Version	Notes
/	Aug. 09, 2023	Valid	Initial release




The photo of the sample



























The photo of AGC05443230802-001 is for use only with the original report.

Test Point Description

Test point	Test module	Test parts	Test point description
8 Digit bamb	ooo calculator Mod	lel: MO6215	
1			Woody shell
2			White plastic shell
3			Double-sided tape
4	Outer shell		Transparent label
5		W	White silicone keypad
6		Key	Black silicone pad
7			Silver screw
8			Solar panels
9			Solder
10		Solar panels	Red wire jacket
11			Black wire jacket
12			Conductor
13			Transparent tape
14			Zebra tape
15		Display nonel	Polarizer
16		Display panel	Glass display screen
17			White plastic sheet
18			Black foam with glue
19			Metallic sheet
20			Solder
21		Battery chip	Red wire jacket
22			Black wire jacket
23			Conductor
24			Black circular IC
25		Circuit board	Chip capacitor
26		Circuit board	PCB
27			Solder

Note: "---" = The test point exists alone in the sample and is not attached to the test module or test parts.



Note: N.D.=Not Detected (less than method detection limit), MDL = Method Detection Limit, 1mg/kg=0.0001%

2011/65/EU (RoHS) and its amendment directive (EU) 2015/863

- Pb, Cd, Hg, Cr⁶⁺, PBBs, PBDEs, DBP, BBP, DEHP, DIBP

Test Item	Test Method/ Instrument	MDL	Maximum Limit
Lead (Pb)		/	1000mg/kg
Cadmium (Cd)		/	100mg/kg
Mercury (Hg)	IEC 62321-3-1:2013/ XRF	/	1000mg/kg
Total Chromium		/	/
Total Bromine		/	/
Chemistry Method			
Lead (Pb)	IEC 62321-5:2013/ ICP-OES	2mg/kg	1000mg/kg
Cadmium (Cd)	IEC 62321-5:2013/ ICP-OES	2mg/kg	100mg/kg
Mercury (Hg)	IEC 62321-4: 2013+A1:2017/ ICP-OES	2mg/kg	1000mg/kg
Non-metal: Hexavalent Chromium (Cr ⁶⁺)	IEC 62321-7-2:2017/ UV-Vis	8mg/kg	1000mg/kg
Metal: Hexavalent Chromium (Cr ⁶⁺)	IEC 62321-7-1:2015/ UV-Vis	0.1μg/cm ²	/
-Monobromobiphenyl (MonoBB) -Dibromobiphenyl (DiBB) -Tribromobiphenyl (TriBB) -Tetrabromobiphenyl (TetraBB) -Pentabromobiphenyl (PentaBB) -Hexabromobiphenyl (HexaBB) -Heptabromobiphenyl (HeptaBB) -Octabromobiphenyl (OctaBB) -Nonabromodiphenyl (NonaBB) -Decabromodiphenyl (DecaBB)	IEC 62321-6:2015/ GC-MS	Single 5mg/kg	Sum 1000mg/kg
PolybrominatedDiphenylethers (PBDEs) -Monobromodiphenyl ether (MonoBDE) -Dibromodiphenyl ether (DiBDE) -Tribromodiphenyl ether (TriBDE) -Tetrabromodiphenyl ether (TetraBDE) -Pentabromodiphenyl ether (PentaBDE) -Hexabromodiphenyl ether (HexaBDE) -Heptabromodiphenyl ether (HeptaBDE) -Octabromodiphenyl ether (OctaBDE) -Nonabromodiphenyl ether (NonaBDE) -Decabromodiphenyl ether (DecaBDE)	IEC 62321-6:2015/ GC-MS	Single 5mg/kg	Sum 1000mg/kg
Di-iso-butyl phthalate (DIBP)		50mg/kg	1000mg/kg
Dibutyl phthalate (DBP)		50mg/kg	1000mg/kg
Butylbenzyl phthalate (BBP)	IEC 62321-8:2017/ GC-MS	50mg/kg	1000mg/kg
Di-(2-ethylhexyl) Phthalate (DEHP)		50mg/kg	1000mg/kg



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	Pb		BL	/	
	(Cd	BL	/	
		łg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
1		PBBs	DI	/	C f : t
1	Br	PBDEs	BL	/	Conformity
	D	BP	N/A	N.D.	
	D	BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	DI	ЕНР	N/A	N.D.	
	I	Pb	BL	/	
	(Cd	BL	/	
-	I	Ig	BL	/	
-		Cr ⁶⁺)	BL	/	
_	·	PBBs		/	Conformity
2	2 Br	PBDEs	BL	/	
-	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
-	DEHP		N/A	N.D.	
	Pb		BL	/	
-	Cd		BL	/	
-	Hg		BL	/	
-	Cr(Cr ⁶⁺)		BL	/	
3	Br	PBBs PBDEs	BL	/	Conformity
-	D	BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		EHP	N/A	53	
		Pb	BL	/	
ļ		Cd Cd	BL	/	
ļ		Ig	BL	/	
ļ		Cr ⁶⁺)	BL	/	
4	Br	PBBs PBDEs	BL	/	Conformity
}	D)	IBP	N/A	N.D.	
}		BP	N/A	N.D.	
<u> </u>		BP	N/A N/A	N.D.	
-		EHP	N/A N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443230802-0 Conclusion
	Pb		BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
5	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	D	ЕНР	N/A	N.D.	
		Pb	BL	/	
	(Cd	BL	/	
]	Hg	BL	/	
		Cr ⁶⁺)	BL	/	
6		PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
-	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	Cr(Cr ⁶⁺)		BL	/	
7	Br	PBBs PBDEs	N/A	/	Conformity
	D	IBP	N/A	/	
	DBP		N/A	/	
		BP	N/A	/	
<u> </u>	DEHP		N/A	/	l
		Pb	BL	/	
ļ		Cd	BL	/	
ļ	Hg		BL	/	
		(Cr ⁶⁺)	BL	/	
8	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
-		ЕНР	N/A	N.D.	



Page 9 of 20

Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
-		(Cr ⁶⁺)	BL	/	
0		PBBs	NT/A	/	G 6 :
9	Br	PBDEs	N/A	/	Conformity
	D	IBP	N/A	/	
	Ι)BP	N/A	/	
	E	BBP	N/A	/	
	D	ЕНР	N/A	/	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr	(Cr^{6+})	BL	/	
10	10 Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	70	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
11	Br	PBBs PBDEs	BL	/	Conformity
	D	DIBP	N/A	N.D.	
		DBP	N/A	N.D.	
		BBP	N/A	N.D.	
	DEHP		N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
F		Hg	BL	/	
		(Cr ⁶⁺)	BL	/	
12	Br PBBs PBDEs		N/A	/	Conformity
	Г	OIBP	N/A	/	
)BP	N/A	/	
-		BBP	N/A	/	
				/	
	D	EHP	N/A	/	



Test point	Tes	t Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443230802-0 Conclusion
	Pb		BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr	(Cr ⁶⁺)	BL	/	
13	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
)BP	N/A	N.D.	
	E	BBP	N/A	N.D.	
	D	ЕНР	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		(Cr^{6+})	BL	/	
14		PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
15	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
)BP	N/A	N.D.	
		BBP	N/A	N.D.	
		ЕНР	N/A	N.D.	
		Pb	BL	/	
	Cd		BL	/	
-		Hg	BL	/	
		(Cr^{6+})	BL	/	
16	Br PBBs PBDEs		BL	/	Conformity
ŀ	n	IBP	N/A	N.D.	
ŀ)BP	N/A	N.D.	
ŀ		BBP	N/A	N.D.	
ŀ		EHP	N/A	N.D.	
	D.	L-111	1 1/ /1	14.1.	



Test point	Tes	t Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443230802-0 Conclusion
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		(Cr^{6+})	BL	/	
17	Br	PBBs	BL	/	Conformity
_		PBDEs DIBP	NT/A	,	
-		OBP	N/A N/A	N.D.	
_					
		BBP	N/A	N.D.	
		EHP	N/A	N.D.	
		Pb	BL	/	
_		Cd	BL	/	
		Hg	BL	/	
-	Cr	(Cr ⁶⁺)	BL	/	
18	18 Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
-	Cd		BL	/	
-	Hg		BL	/	
-	$Cr(Cr^{6+})$		BL	/	
19	Br	PBBs PBDEs	N/A	/	Conformity
	Γ	OIBP	N/A	/	
		OBP	N/A	/	
			N/A	/	
	BBP DEHP		N/A	/	
		Pb	BL	/	
-		Cd	BL	/	
-		Hg	BL	/	
		$\frac{\operatorname{rig}}{(\operatorname{Cr}^{6+})}$		/	
-	Cr		BL	/	
20	Br	PBBs PBDEs	N/A	/	Conformity
	т-		NT/A	/	
-		OIBP	N/A	/	
-		OBP OBD	N/A	/	
		BBP	N/A	/	
	D	EHP	N/A	/	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	Pb		BL	/	
	(Cd	BL	/	
	F	Ig	BL	/	
	Cr(0	Cr^{6+})	BL	/	
21		PBBs	DI	/	
21	Br	PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
	D	BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	DE	CHP	N/A	N.D.	
	F	Pb	BL	/	
	C	Cd	BL	/	
	F	lg	BL	/	
		Cr ⁶⁺)	BL	/	
		PBBs		/	Conformity
22	22 Br	PBDEs	BL	/	
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
23	Br	PBBs PBDEs	N/A	/	Conformity
	DI	BP	N/A	/	
	DBP		N/A	/	
		BP	N/A	/	
		НР	N/A	/	
		rb	BL	/	
		Cd	BL	/	
	Hg		BL	/	
		Cr^{6+})	BL	/	
24	p_{RR_c}		BL	/	Conformity
-	וח	BP	N/A	N.D.	
-		BP	N/A	N.D.	
-		BP	N/A N/A	N.D.	
_		CHP	N/A N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443230802-00 Conclusion
	I	b	BL	/	
	(Cd	BL	/	
		Ig	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
25	Br	PBBs	BL	/	Conformity
23	BI	PBDEs	BL	/	Conformity
	Dl	BP	N/A	N.D.	
	D	BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	DE	ЕНР	N/A	N.D.	
	Pb Cd		BL	/	
			BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
26	Br	PBBs	BL	/	Conformity
20		PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	I	Pb	BL	/	
	Cd		BL	/	
	I	Ig	BL	/	
27	Cr(Cr ⁶⁺)	BL	/	
	Br	PBBs PBDEs	N/A	/	Conformity
	Di	BP	N/A	/	
		BP	N/A	/	
		BP	N/A	/	
		CHP	N/A	/	

Element	Unit	Non-metal	Metal	Composite Material
Cd	mg/kg	BL≤70-3σ <x <130+3σ≤OL</x 	BL≤70-3σ <x <130+3σ≤OL</x 	BL≤50-3σ <x <150+3σ≤OL</x
Pb	mg/kg	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤500-3σ <x <1500+3σ≤OL</x
Hg	mg/kg	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤500-3σ <x <1500+3σ≤OL</x
Cr	mg/kg	BL≤700-3σ <x< td=""><td>BL≤700-3σ<x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<></td></x<>	BL≤700-3σ <x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<>	BL≤500-3σ <x< td=""></x<>



		Керо	11 110 110003443230002-001	
Br	mg/kg	BL≤300-3σ <x< th=""><th>N/A</th><th>BL≤250-3σ<x< th=""></x<></th></x<>	N/A	BL≤250-3σ <x< th=""></x<>

Report No · AGC05///3230802-001

Remark:

- (1) BL= Below Limit, OL= Over limited, IN = Inconclusive, Scanning by XRF and detected by chemical method, N/A = Not applicable.
- (2) Results were obtained by XRF for primary scanning, and further chemical testing by ICP (for Cd, Pb, Hg), UV-Vis (for Cr(VI)) and GC-MS (for PBBs, PBDEs) are recommended to be performed, if the concentration exceeds the above warning value.
- (3) The XRF scanning test for RoHS elements The reading may be different to the actual content in the sample be of non-uniformity composition.
- (4) Boiling-water-extraction:(X represents the results of the tested sample)

Number	Colorimetric result (Cr(VI) concentration)	Judgement
1	$X < 0.1 \mu g/cm^2$	Negative
2	$0.1 \mu g/cm^2 \le X \le 0.13 \mu g/cm^2$	Uncertainty
3	$X>0.13\mu g/cm^2$	Positive

Negative indicates the absence of Cr(VI) on the tested areas concentration is below the limit of quantification. The coating is considered a non-Cr(VI) based coating.

Uncertainty indicates the absence of Cr(VI) on the tested areas unavoidable coating variations may influence the determination.

Positive indicates the presence of Cr(VI) on the tested areas concentration is above the limit of quantification and the statistical margin of error. The sample coating is considered to contain Cr(VI).

Storage conditions and production date of the tested sample are unavailable and thus result of Cr(VI) represent status of the sample at the time of testing.

(5) Disclaimers: This XRF Scanning report is for reference purposes only. The applicant shall make its/his/her own judgment as to whether the information provided in this XRF screening report is sufficient for its/his/her purposes. The result shown in this XRF scanning report will differ based on various factors, including but not limited to, the sample size, thickness, area, surface flatness, equipment parameters and matrix effect (e.g. plastic, rubber, metal, glass, ceramic etc.). Further wet chemical pre-treatment with relevant chemical equipment analysis are required to obtain quantitative data.

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50

- Polycyclic-aromatic Hydrocarbons (PAHs) Content

Test Methods and Equipment: Afps GS 2019:01 PAK; GC-MS

Tost Itom(s)	Unit Limit MDL		MDL	Test Resi	ult(s)
Test Item(s)	Unit	Lillit	MDL	2	5
Benzo[a]pyrene(BaP)	mg/kg	1	0.1	N.D.	N.D.
Benzo[e]pyrene(BeP)	mg/kg	1	0.1	N.D.	N.D.
Benzo[a]anthracene(BaA)	mg/kg	1	0.1	N.D.	N.D.
Benzo[b]fluoranthene(BbF)	mg/kg	1	0.1	N.D.	N.D.
Benzo[j]fluoranthene(BjFA)	mg/kg	1	0.1	N.D.	N.D.
Benzo[k]fluoranthene(BkF)	mg/kg	1	0.1	N.D.	N.D.
Chrysene(CHR)	mg/kg	1	0.1	N.D.	N.D.
Dibenzo[a,h]anthracene(DBA)	mg/kg	1	0.1	N.D.	N.D.
Conclusion				Conformity	Conformity



Limit requirements of Polycyclic-aromatic Hydrocarbons (PAHs) (Unit: mg/kg)

<u> </u>				<i>8 8</i> /
Items	CAS No.	Extender oils or used for the production of tyres or parts of tyres	Any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity	Toys, including activity toys, and childcare articles, any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity
Benzo[a]pyrene(BaP)	50-32-8	≤ 1	≤ 1	≤ 0.5
Benzo[e]pyrene(BeP)	192-97-2	/	≤ 1	≤ 0.5
Benzo[a]anthracene(BaA)	56-55-3	/	≤ 1	≤ 0.5
Benzo[b]fluoranthene(BbF)	205-99-2	/	≤ 1	≤ 0.5
Benzo[j]fluoranthene(BjFA)	205-82-3	/	≤ 1	≤ 0.5
Benzo[k]fluoranthene(BkF)	207-08-9	/	≤ 1	≤ 0.5
Chrysene(CHR)	218-01-9	/	≤ 1	≤ 0.5
Dibenzo[a,h]anthracene(DBA)	53-70-3	/	≤ 1	≤ 0.5
Sum of BaP+ BeP+ BaA+ BbF+ BjFA+ BkF+ CHR+ DBA	/	≤ 10	/	/

Regulation (EU) 2019/1021 on persistent organic pollutants (POPs)

- Pentachlorophenol (PCP) Content


Test Methods and Equipment: EPA 3550C:2007 & EPA 8270E:2018; GC-MS

Tost Itom(s)	Unit	Limit	MDL	Test Result(s)
Test Item(s)				1
Pentachlorophenol (PCP)	mg/kg	5	5	N.D.
Со	Conformity			

- Formaldehyde Release


Test Methods and Equipment: EN 717-3:1996; UV-Vis

Tost Itom(s)	Unit	Client's	MDL	Test Result(s)
Test Item(s)		limit		1
Formaldehyde Release	mg/kg	80	1	4
Со	Conformity			







Test Flow Chart of XRF




Test Flow Chart of Phthalates









Test Flow Chart of Polycyclic-aromatic Hydrocarbons (PAHs)









Test Flow Chart of Pentachlorophenol (PCP)







Test Flow Chart of Formaldehyde Release





Conditions of Issuance of Test Reports

- 1. All samples and goods are accepted by the Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd. (the "Company") solely for testing and reporting in accordance with the following terms and conditions. The company provides its services on the basis that such terms and conditions constitute express agreement between the company and any person, firm or company requesting its services (the "Clients").
- 2. Any report issued by Company as a result of this application for testing services (the "Report") shall be issued in confidence to the Clients and the Report will be strictly treated as such by the Company. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of the Company. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by the Company to its customer, supplier or other persons directly concerned. The Company will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the Report, unless required by the relevant governmental authorities, laws or court orders.
- 3. The Company shall not be called or be liable to be called to give evidence or testimony on the Report in a court of law without its prior written consent, unless required by the relevant governmental authorities, laws or court orders.
- 4. In the event of the improper use of the report as determined by the Company, the Company reserves the right to withdraw it, and to adopt any other additional remedies which may be appropriate.
- 5. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Company.
- 6. The Company will not be liable for or accept responsibility for any loss or damage however arising from the use of information contained in any of its Reports or in any communication whatsoever about its said tests or investigations. 7. Clients wishing to use the Report in court proceedings or arbitration shall inform the Company to that effect prior to submitting the sample for testing.
- 8. The Company is not responsible for recalling the electronic version of the original report when any revision is made to them. The Client assumes the responsibility to providing the revised version to any interested party who uses them.
- 9. Subject to the variable length of retention time for test data and report stored hereinto as otherwise specifically required by individual accreditation authorities, the Company will only keep the supporting test data and information of the test report for a period of six years. The data and information will be disposed of after the aforementioned retention period has elapsed. Under no circumstances shall we provide any data and information which has been disposed of after retention period. Under no circumstances shall we be liable for damage of any kind, including (but not limited to) compensatory damages, lost profits, lost data, or any form of special, incidental, indirect, consequential or punitive damages of any kind, whether based on breach of contract of warranty, tort (including negligence), product liability or otherwise, even if we are informed in advance of the possibility of such damages.

*** End of Report ***