

RoHS Test Report

Report No. : AGC05443221125-001

- SAMPLE NAME : Sunset Projection lamp
- MODEL NAME : MO6766
- **APPLICANT** : MID OCEAN BRANDS B.V
- **STANDARD(S)** : Please refer to the following page(s).
- **DATE OF ISSUE** : Dec. 09, 2022





Applicant	:	MID OCEAN BRANDS B.V
Address	:	7/F, Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong.
Test Site	:	6/F., Building 2, Sanwei Chaxi Industrial Park, Sanwei Community, Hangcheng
		Street, Bao'an District, Shenzhen, Guangdong, China

Report on the submitted sample(s) said to be:

Sample Name	:	Sunset Projection lamp
Model	:	MO6766
Vendor code	:	106613
Country of Origin	:	CHINA
Country of Destination	:	EUROPE
Sample Received Date	:	Nov. 24, 2022
Testing Period	:	Nov. 24, 2022 to Dec. 09, 2022
Test Requested	:	Selected test(s) as requested by client.

Test Requested:

Conclusion

Pass

2011/65/EU (RoHS) and its amendment directive (EU) 2015/863 - Pb, Cd, Hg, Cr⁶⁺, PBBs, PBDEs, DBP, BBP, DEHP, DIBP

Approved by : Jossie ling

Liangdan, Jessie.Liang


Technical Director



Report Revise Record

		F	
Report Version	Issued Date	Valid Version	Notes
/	Dec. 09, 2022	Valid	Initial release






The photo of the sample







The photo of AGC05443221125-001 is for use only with the original report.

60 10

50 mm

40 30

20

0

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

10 20 30 40 50 90 70 80 90100 10 20 30 40

0 50 30 40 20 60 10 80 30 100 10 50 30 40 20 60 10 80

ոկավավակակակովորկակակակակակություն։

8: 0 4 0 150X



Test Point D Test point	Test module	Test parts	Test point description
Sunset Proj		Test parts	Test point description
1			Black plastic shell
2		Base	Ballast block
2 3			Black screw
4 5	_		Black plastic rod Metallic screw
		Screw	
6	Stand		Black plastic
7	_		Metal threaded ring
8			Black screw
9		_	Transparent plastic lampshade
10		Lamp housing	Multicolored plastic sheet
11			Black plastic shell
12			Metal threaded ring
13			Chip LED
14		Lamp board	Chip resistor
15			Metal aluminum plate
16			Solder
17			USB metal plug
18		USB plug	White plastic plug
19			Pin
20			Black handle
21			Solder
22		Case for voice controller	Black plastic shell
23			Black plastic button
24			Metal spring
25			Metal base
26		- Switch	Black plastic shell
27			Metallic sheet
28			Solder
29			Black outer wire jacket
30			Black wire jacket
31		Wire rod	Red wire jacket
32			Conductor
Remote con	itrol		
33			Key panel film
34		Outer shell	Double-sided tape
35			Black plastic shell
36			Metallic shrapnel
37	1		Metal spring
38	Circuit board		IC body
39	-1	IC	Metallic pin with solder
57			mounte pin with solder

		Report No.: AGC05443221125-001 Page 7 of 25
40		Solder
41	T., 1: 1: - 1-4	LED body
42	Indicator light	Metal pin
43		Green PCB

Note: "---" = The test point exists alone in the sample and is not attached to the test module or test parts.

Test Results:

Note: N.D.=Not Detected (less than method detection limit), MDL = Method Detection Limit %= percentage (W/W)

2011/65/EU (RoHS) and its amendment directive (EU) 2015/863

- Pb, Cd, Hg, Cr⁶⁺, PBBs, PBDEs, DBP, BBP, DEHP, DIBP

Test Item	Test Method/ Instrument	MDL	Maximum Limit
Lead (Pb)		/	1000mg/kg
Cadmium (Cd)		/	100mg/kg
Mercury (Hg)	IEC 62321-3-1:2013/ XRF	/	1000mg/kg
Total Chromium		/	/
Total Bromine		/	/
Chemistry Method			
Lead (Pb)	IEC 62321-5:2013/ ICP-OES	10mg/kg	1000mg/kg
Cadmium (Cd)	IEC 62321-5:2013/ ICP-OES	10mg/kg	100mg/kg
Mercury (Hg)	IEC 62321-4: 2013+A1:2017/ ICP-OES	10mg/kg	1000mg/kg
Non-metal Hexavalent Chromium (Cr ⁶⁺)	IEC 62321-7-2:2017/ UV-Vis	8mg/kg	1000mg/kg
Metal Hexavalent Chromium (Cr ⁶⁺)	IEC 62321-7-1:2015/ UV-Vis	0.1µg/cm ²	/
Polybrominated Biphenyls (PBBs) -Monobromobiphenyl (MonoBB) -Dibromobiphenyl (DiBB) -Tribromobiphenyl (TriBB) -Tetrabromobiphenyl (TetraBB) -Pentabromobiphenyl (PentaBB) -Hexabromobiphenyl (HexaBB) -Heptabromobiphenyl (HeptaBB) -Octabromobiphenyl (OctaBB) -Nonabromodiphenyl (NonaBB) -Decabromodiphenyl (DecaBB)	IEC 62321-6:2015/ GC-MS	Single 5mg/kg	Sum 1000mg/kg



Test Item	Test Method/ Instrument	MDL	Maximum Limit
PolybrominatedDiphenylethers (PBDEs)-Monobromodiphenyl ether (MonoBDE)-Dibromodiphenyl ether (DiBDE)-Tribromodiphenyl ether (TriBDE)-Tetrabromodiphenyl ether (TetraBDE)-Pentabromodiphenyl ether (PentaBDE)-Hexabromodiphenyl ether (HexaBDE)-Heptabromodiphenyl ether (HeptaBDE)-Octabromodiphenyl ether (OctaBDE)-Nonabromodiphenyl ether (NonaBDE)-Decabromodiphenyl ether (DecaBDE)	IEC 62321-6:2015/ GC-MS	Single 5mg/kg	Sum 1000mg/kg
Di-iso-butyl phthalate (DIBP)		50mg/kg	1000mg/kg
Dibutyl phthalate (DBP)	IEC 62321-8:2017/ GC-MS	50mg/kg	1000mg/kg
Butylbenzyl phthalate (BBP)	1EC 02321-0.2017/ GC-MS	50mg/kg	1000mg/kg
Di-(2-ethylhexyl) Phthalate (DEHP)		50mg/kg	1000mg/kg



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion	
	Pb		BL	/		
	0	Cd	BL	/		
	H	Ig	BL	/		
	Cr(0	Cr ⁶⁺)	BL	/		
1	D	PBBs	DI	N.D.		
1	Br	PBDEs	IN	155	Conformity	
	DI	BP	N/A	N.D.		
	D	BP	N/A	N.D.		
	B	BP	N/A	N.D.		
	DE	HP	N/A	83		
	F	Ъ	BL	/		
	0	Cd	BL	/		
	H	Ig	BL	/		
	Cr(0	Cr ⁶⁺)	BL	/		
2	Da	PBBs	BL	/	Conformator	
Z	Br	PBDEs	BL	/	Conformity	
	DIBP		N/A	N.D.		
	D	BP	N/A	N.D.		
	BBP		N/A	N.D.		
	DE	CHP	N/A	N.D.		
	F	Ъ	BL	/		
	0	Cd	BL	/		
	Hg		BL	/		
	Cr(0	Cr^{6+})	BL	/		
3	Br	PBBs PBDEs	N/A	/ /	Conformity	
	DI	BP	N/A	/		
	D	BP	N/A	/		
	B	BP	N/A	/		
	DE	EHP	N/A	/		
	F	'b	BL	/		
	0	Cd	BL	/		
	H	Ig	BL	/		
	Cr(0	Cr ⁶⁺)	BL	/		
4	Br PBBs PBDEs		BL	/ /	Conformity	
	DI	BP	N/A	N.D.		
		BP	N/A	N.D.		
		BP	N/A	N.D.		
		CHP	N/A	143		



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	Рb		BL	/	
	(Cd	BL	/	
	H	łg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
5	Br	PBBs PBDEs	N/A	/	Conformity
	D	BP	N/A	/	
		BP	N/A	/	
		BP	N/A	/	
		EHP	N/A	/	
		°b	BL	/	
		Cd	BL	/	
		Ig	BL	/	
		Cr^{6+}	BL	/	
	CI	PBBs		N.D.	
6	Br	PBDEs	IN	N.D.	Conformity
			N/A	N.D.	
	DIBP DBP BBP		N/A N/A	N.D.	
			N/A N/A	N.D.	
		EHP	N/A N/A	67	
		Pb	BL	/	
		Cd	BL	/	
			BL	/	
		$\operatorname{Ig}_{\operatorname{C}^{*6^+}}$	BL	/	
7	Cr(0	PBBs	N/A	/	Conformity
/	Br PBDEs		IN/A	/	Conformity
	D	BP	N/A	/	
	D	BP	N/A	/	
	BBP		N/A	/	
	DH	ЕНР	N/A	/	
	I	Ъ	BL	/	
	(Cd	BL	/	
	ŀ	łg	BL	/	
		Cr ⁶⁺)	BL	/	
8	Br PBBs PBDEs		N/A	/	Conformity
	וח	BP	N/A	/	
		BP	N/A	/	
		BP	N/A N/A	/	
		EHP	N/A N/A	/	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	I	Ъ	BL	/	
	(Cd	BL	/	
	ŀ	Ig	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
9	Br	PBBs PBDEs	BL	/	Conformity
	D	BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		EHP	N/A	N.D.	
		ур. Ур.	BL	/	
		Cd	BL	/	
		Ig	BL	/	
		Cr^{6+}	BL	/	
10		PBBs		/	
10	Br	PBDEs	BL	/	Conformity
	DIBP DBP BBP		N/A	N.D.	
			N/A	N.D.	
			N/A	N.D.	
	DEHP		N/A	N.D.	
		Ъ.	BL	/	
	Cd		BL	/	
	Hg		BL	/	
	Cr(Cr ⁶⁺)		BL	/	
	PBBs			N.D.	
11	Br	PBDEs	IN	102	Conformity
	D	BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		EHP	N/A	N.D.	
		ун Рb	BL	/	
		Cd	BL	/	
		Ig	BL	/	
-		Cr^{6+}	BL	/	
		PBBs		/	
12	Br	PBDEs	N/A	/	Conformity
	וח	BP	N/A	/	
		BP	N/A N/A	/	
			N/A N/A	/	
	BBP DEHP		N/A N/A	/	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion	
	Pb		BL	/		
	(Cd	BL	/		
	I	Hg	BL	/		
	Cr(Cr ⁶⁺)	BL	/		
13	Br	PBBs PBDEs	BL	/	Conformity	
	D	IBP	N/A	N.D.		
		BP	N/A	N.D.		
		BP	N/A	N.D.		
		EHP	N/A	N.D.		
		Pb	IN	58251		
		Cd	BL	/		
		-Jg	BL	/		
		$\frac{rg}{Cr^{6+}}$	BL	/		
		PBBs	DL	/	Conformity	
14	Br	PBDEs	BL	/	Exemption	
	DIBP		N/A	N.D.	clause 7(c)-l	
		BP	N/A N/A	N.D.		
			N/A N/A	N.D.		
	BBP DEHP					
		Pb	N/A BL	N.D.		
				/		
		Cd	BL	/		
	Hg Cr(Cr ⁶⁺)		BL	/		
	Cr(-	BL	/		
15	Br	PBBs PBDEs	N/A	/	Conformity	
	D	IBP	N/A	/		
	D	BP	N/A	/		
	BBP		N/A	/		
	DI	EHP	N/A	/		
]	Pb	BL	/		
	(Cd	BL	/		
	I	Нg	BL	/		
	Cr(Cr ⁶⁺)	BL	/		
16	Br PBBs PBDEs		N/A	/	Conformity	
	D	IBP	N/A	/		
		BP	N/A	/		
		BP	N/A	/		
		EHP	N/A N/A	/		



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	РЪ		BL	/	
	(Cd	BL	/	
	Hg		BL	/	
		Cr ⁶⁺)	BL	/	
17	Br	PBBs PBDEs	N/A	/	Conformity
	D	BP	N/A	/	
		BP	N/A	/	
·		BP	N/A	/	
		EHP	N/A	/	
		Ъ	BL	/	
		Cd	BL	/	
		łg	BL	/	
		Cr ⁶⁺)	BL	/	
		PBBs		/	
18	Br	PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DI	EHP	N/A	N.D.	
		Ъ	BL	/	
	(Cd	BL	/	
	Hg		BL	/	
		Cr ⁶⁺)	BL	/	
19	Br	PBBs PBDEs	N/A	/	Conformity
	D	BP	N/A	/	
	D	BP	N/A	/	
		BP	N/A	/	
	DEHP		N/A	/	
	I	Ъ	BL	/	
	(Cd	BL	/	
	H	łg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
20	Br PBBs PBDEs		BL	/ /	Conformity
	D	BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		ЕНР	N/A	N.D.	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	P	'b	BL	/	
	C	Cd	BL	/	
	H	[g	BL	/	
	Cr(0	Cr ⁶⁺)	BL	/	
21	Br	PBBs PBDEs	N/A	/	Conformity
	DI	BP	N/A	/	
		BP	N/A	/	
		BP	N/A	/	
		HP	N/A	/	
		'b	BL	/	
		ùd	BL	/	
		[g	BL	/	
		Cr^{6+})	BL	/	
	Br PBDEs			/	Conformity
22			BL	/	
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	94	
		'b	BL	/	
		čd	BL	/	
	Hg		BL	/	
	Cr(Cr ⁶⁺)		BL	/	
23	Br	PBBs PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
	DBP		N/A	N.D.	
		BP	N/A	N.D.	
		HP	N/A	N.D.	
		'b	BL	/	
		čd	BL	/	
	Hg		BL	/	
24	Cr(Cr ⁶⁺)		BL	/	
	Br	PBBs PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
		BP	N/A	/	
		BP	N/A	/	
		CHP	N/A	/	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	I	Ъ	BL	/	
	(Cd	BL	/	
	ŀ	Ig	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
25	Br	PBBs PBDEs	N/A	/	Conformity
	D	BP	N/A	/	
		BP	N/A	/	
		BP	N/A	/	
		EHP	N/A	/	
		Ъ	BL	/	
		Cd	BL	/	
		łg	BL	/	
		Cr^{6+}	BL	/	
		PBBs		/	Conformity
26	Br	PBDEs	BL	/	
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
-	DEHP		N/A	N.D.	
		ун Р	BL	/	
		Cd	BL	/	
	Hg		BL	/	
	Cr(Cr ⁶⁺)		BL	/	
27	Br	PBBs PBDEs	N/A	/	Conformity
	D	BP	N/A	/	
	DBP		N/A	/	
		BP	N/A	/	
		EHP	N/A	/	
		°b	BL	/	
		Cd	BL	/	
	Hg		BL	/	
	Cr(Cr ⁶⁺)		BL	/	
28	Br	PBBs PBDEs	N/A	/	Conformity
	וח	BP	N/A	/	
		BP	N/A N/A	/	
		BP	N/A N/A	/	
		EHP	N/A N/A	/	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	P	b	BL	/	
	C	Cd	BL	/	
	H	[g	BL	/	
	Cr(0	Cr ⁶⁺)	BL	/	
29	Br	PBBs PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		CHP	N/A	N.D.	
		'b	BL	/	
		zd	BL	/	
		[g	BL	/	
		Cr^{6+}	BL	/	
	CI(C	PBBs	BL	/	Conformity
30	Br	PBDEs	BL	/	
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
-	DEHP		N/A	N.D.	
		'b	BL	/	
·		Cd	BL	/	
	Hg		BL	/	
·	Cr(Cr ⁶⁺)		IN	N.D.	
31	Br	PBBs PBDEs	BL	/	Conformity
·	DI	BP	N/A	N.D.	
	DBP		N/A	N.D.	
		BP	N/A	N.D.	
		НР	N/A	N.D.	
		'b	BL	/	
		2d	BL	/	
	Hg		BL	. /	
	$Cr(Cr^{6+})$		BL	/	
32	Br	PBBs PBDEs	N/A	/	Conformity
	וח	BP	N/A	/	
		BP	N/A N/A	/	
		BP	N/A N/A	/	
		HP	N/A N/A	/	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	F	'b	BL	/	
	C	Cd	BL	/	
	H	Ig	BL	/	
	Cr(0	Cr ⁶⁺)	BL	/	
33	Br	PBBs PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		EHP	N/A	N.D.	
		Ъ.	BL	/	
		Cd	BL	/	
		Ig	BL	/	
		Cr^{6+}	BL	/	
		PBBs	BL	/	Conformity
34	Br	PBDEs		/	
	DIBP		N/A	, N.D.	
	DBP		N/A N/A	N.D.	
	BBP		N/A N/A	N.D.	
_	DEHP		N/A N/A	N.D.	
		инг Рb	BL	N.D.	
			BL BL	/	
	Cd		BL BL	/	
	Hg Cr(Cr ⁶⁺)			/	
	Cr(C		BL - IN -		
35	Br —	PBBs		N.D.	Conformity
		PBDEs	N T / A	859	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
	BBP		N/A	N.D.	
		EHP	N/A	N.D.	
		^v b	BL	/	
	Cd Hg		BL	/	
			BL	/	
	Cr(0	Cr ⁶⁺)	IN	N.D.	
36	Br PBBs PBDEs		N/A	/	Conformity
	DI	BP	N/A	/	
		BP	N/A	/	
		BP	N/A	/	
		EHP	N/A	/	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	F	'b	BL	/	
	0	Cd	BL	/	
	H	Ig	BL	/	
	Cr(0	Cr ⁶⁺)	BL	/	
37	Br	PBBs PBDEs	N/A	/	Conformity
	DI	BP	N/A	/	
		BP	N/A	/	
		BP	N/A	/	
		EHP	N/A	/	
		°b	BL	/	
		Cd	BL	/	
		Ig	BL	/	
		Cr^{6+}	BL	/	
	CI(PBBs		/	Conformity
38	Br —	PBDEs	BL	/	
	DIBP		N/A	N.D.	
	DBP		N/A N/A	N.D.	
	BBP		N/A N/A	N.D.	
-	DEHP		N/A N/A	N.D.	
		b	BL	N.D.	
		Cd	BL	/	
			BL	/	
	Hg Cr(Cr ⁶⁺)		BL	/	
39	Br	PBBs PBDEs	N/A	/	Conformity
	וח		N/A	/	
	DIBP DBP		N/A	/	
			N/A N/A	/	
	BBP DEHP		N/A	/	
		b	BL	/	
			BL	/	
	Cd		BL	/	
	Hg		BL	/	
	Cr(Cr ⁶⁺) Br PBBs PBDEs DIBP		DL	/	
40			N/A	/	Conformity
			N/A	/	
		BP	N/A	/	
		BP	N/A N/A	/	
		EHP	N/A N/A	/ /	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF)	Wet Chemistry Method	Conclusion
			mg/kg	mg/kg	
	I	Ъ	BL	/	
	(Cd	BL	/	
		Ig	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
41	Br	PBBs	IN	N.D.	Conformity
41	DI	PBDEs	111	N.D.	Comornity
	D	BP	N/A	N.D.	
	D	BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	DE	EHP	N/A	N.D.	
	I	°b	BL	/	
	(Cd	BL	/	
	Hg Cr(Cr ⁶⁺)		BL	/	
			IN	N.D.	
42	Br	PBBs	- N/A	/	Conformity
42		PBDEs		/	
	DIBP		N/A	/	
	DBP BBP		N/A	/	
			N/A	/	
	DEHP		N/A	/	
	I	Ъ	BL	/	
	Cd Hg Cr(Cr ⁶⁺)		BL	/	1
			BL	/	
			BL	/	
43	Br PBBs PBDEs	PBBs	BL	/	Conformite
43		PBDEs		/	Conformity
	DIBP		N/A	N.D.	
	D	BP	N/A	N.D.	
	B	BP	N/A	N.D.	
	DE	EHP	N/A	N.D.	

Test result on specimen No.16, No.21, No.28, No.39, No.40 were resubmitted on Dec.07, 2022.



Element	Unit	Non-metal	Metal	Composite Material
Cd	mg/kg	BL≤70-3σ <x <130+3σ≤OL</x 	BL≤70-3σ <x <130+3σ≤OL</x 	BL≤50-3σ <x <150+3σ≤OL</x
Pb	mg/kg	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤500-3σ <x <1500+3σ≤OL</x
Hg	mg/kg	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤500-3σ <x <1500+3σ≤OL</x
Cr	mg/kg	BL≤700-3σ <x< td=""><td>BL≤700-3σ<x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<></td></x<>	BL≤700-3σ <x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<>	BL≤500-3σ <x< td=""></x<>
Br	mg/kg	BL≤300-3σ <x< td=""><td>N/A</td><td>BL≤250-3σ<x< td=""></x<></td></x<>	N/A	BL≤250-3σ <x< td=""></x<>

Remark:

- (1) BL= Below Limit, OL= Over limited, IN = Inconclusive, Scanning by XRF and detected by chemical method, N/A = Not applicable.
- (2) Results were obtained by XRF for primary scanning, and further chemical testing by ICP (for Cd, Pb, Hg), UV-Vis (for Cr(VI)) and GC-MS (for PBBs, PBDEs) are recommended to be performed, if the concentration exceeds the above warning value.
- (3) The XRF scanning test for RoHS elements The reading may be different to the actual content in the sample be of non-uniformity composition.
- (4) Boiling-water-extraction:(X represents the results of the tested sample)

Number	Colorimetric result (Cr(VI) concentration)	Judgement
1	$X \le 0.1 \mu g/cm^2$	Negative
2	$0.1\mu g/cm^2 \le X \le 0.13\mu g/cm^2$	Uncertainty
3	$X > 0.13 \mu g/cm^2$	Positive

Negative indicates the absence of Cr(VI) on the tested areas concentration is below the limit of quantification. The coating is considered a non-Cr(VI) based coating.

Uncertainty indicates the absence of Cr(VI) on the tested areas unavoidable coating variations may influence the determination.

Positive indicates the presence of Cr(VI) on the tested areas concentration is above the limit of quantification and the statistical margin of error. The sample coating is considered to contain Cr(VI).

Storage conditions and production date of the tested sample are unavailable and thus result of Cr(VI) represent status of the sample at the time of testing.

(5) Disclaimers: This XRF Scanning report is for reference purposes only. The applicant shall make its/his/her own judgment as to whether the information provided in this XRF screening report is sufficient for its/his/her purposes.

The result shown in this XRF scanning report will differ based on various factors, including but not limited to, the sample size, thickness, area, surface flatness, equipment parameters and matrix effect (e.g. plastic, rubber, metal, glass, ceramic etc.). Further wet chemical pre-treatment with relevant chemical equipment analysis are required to obtain quantitative data.


Exemption clause	Exemption
7(c)-I	Electrical and electronic components containing lead in a glass or ceramic other than dielectric ceramic in capacitors, e.g. piezoelectronic devices, or in a glass or ceramic matrix compound

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.


Attestation of Global Compliance(Shenzhen)Co., Ltd



Test Flow Chart of XRF





Test Flow Chart of Phthalates






Test Flow Chart of PBBs and PBDEs






Test Flow Chart of Hexavalent Chromium (Cr⁶⁺)





Test Flow Chart of Hexavalent Chromium (Cr⁶⁺)





Test Flow Chart of Lead, Cadmium and Mercury

These sample were dissolved totally by pre-conditioning method according to above flow chart



Conditions of Issuance of Test Reports

1. All samples and goods are accepted by the Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd. (the "Company") solely for testing and reporting in accordance with the following terms and conditions. The company provides its services on the basis that such terms and conditions constitute express agreement between the company and any person, firm or company requesting its services (the "Clients").

2. Any report issued by Company as a result of this application for testing services (the "Report") shall be issued in confidence to the Clients and the Report will be strictly treated as such by the Company. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of the Company. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by the Company to its customer, supplier or other persons directly concerned. The Company will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the Report, unless required by the relevant governmental authorities, laws or court orders.

3. The Company shall not be called or be liable to be called to give evidence or testimony on the Report in a court of law without its prior written consent, unless required by the relevant governmental authorities, laws or court orders.

4. In the event of the improper use of the report as determined by the Company, the Company reserves the right to withdraw it, and to adopt any other additional remedies which may be appropriate.

5. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Company.

6. The Company will not be liable for or accept responsibility for any loss or damage however arising from the use of information contained in any of its Reports or in any communication whatsoever about its said tests or investigations.

7. Clients wishing to use the Report in court proceedings or arbitration shall inform the Company to that effect prior to submitting the sample for testing.

8. The Company is not responsible for recalling the electronic version of the original report when any revision is made to them. The Client assumes the responsibility to providing the revised version to any interested party who uses them.

9. Subject to the variable length of retention time for test data and report stored hereinto as otherwise specifically required by individual accreditation authorities, the Company will only keep the supporting test data and information of the test report for a period of six years. The data and information will be disposed of after the aforementioned retention period has elapsed. Under no circumstances shall we provide any data and information which has been disposed of after retention period. Under no circumstances shall we be liable for damage of any kind, including (but not limited to) compensatory damages, lost profits, lost data, or any form of special, incidental, indirect, consequential or punitive damages of any kind, whether based on breach of contract of warranty, tort (including negligence), product liability or otherwise, even if we are informed in advance of the possibility of such damages.

*** End of Report ***

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Attestation of Global Compliance(Shenzhen)Co., Ltd Attestation of Global Compliance(Shenzhen)Std & Tech Co., Ltd